



Product Information for: P0350P1G

Fibre Blend:	Polyester	
Scrim Type:	Polyester	
Finish:	Superglaze	
Chemical Treatment:		
Weight (ISO 9073-1):	350 g/m ²	
Thickness:	1.15 mm	
Permeability (ISO 9237):	225 l/dm ² /min (380 mm/s) @ 200 Pa	
Electrical Resistance (DIN 54345-5):	N/A	
	Machine	Cross
	Direction	Direction
Strength N / 5cm (ISO 9073-3):	1,650	1,125
Strain at 50N / 5cm (%) :	0.4	1.1
Strain at Peak (%) :	26.0	39.0
Shrinkage at 170°C (%) :	2.2	1.6

°Celsius	80	90	100	110	120	130	140	150	160	170	180	190	200	210	220	230	240	250	260	270	280	290											
<table border="1"> <tr> <td>ACIDS</td> <td>ALKALIS</td> <td>OXIDISING AGENTS</td> <td>HYDROLYSIS</td> <td>SOLVENTS</td> <td rowspan="2">AVOID STRONG ALKALI AND ACID ENVIRONMENTS AT ELEVATED TEMPERATURES - THE MOST VERSATILE OF THE LOW TEMPERATURE FIBRES, USED IN THE CEMENT AND QUARRY, METAL PROCESSING, FLOUR AND WOOD INDUSTRIES</td> </tr> <tr> <td>GOOD</td> <td>FAIR</td> <td>GOOD</td> <td>POOR</td> <td>GOOD</td> </tr> </table>																							ACIDS	ALKALIS	OXIDISING AGENTS	HYDROLYSIS	SOLVENTS	AVOID STRONG ALKALI AND ACID ENVIRONMENTS AT ELEVATED TEMPERATURES - THE MOST VERSATILE OF THE LOW TEMPERATURE FIBRES, USED IN THE CEMENT AND QUARRY, METAL PROCESSING, FLOUR AND WOOD INDUSTRIES	GOOD	FAIR	GOOD	POOR	GOOD
ACIDS	ALKALIS	OXIDISING AGENTS	HYDROLYSIS	SOLVENTS	AVOID STRONG ALKALI AND ACID ENVIRONMENTS AT ELEVATED TEMPERATURES - THE MOST VERSATILE OF THE LOW TEMPERATURE FIBRES, USED IN THE CEMENT AND QUARRY, METAL PROCESSING, FLOUR AND WOOD INDUSTRIES																												
GOOD	FAIR	GOOD	POOR	GOOD																													
																																	

Revision Date: 19/12/2014

The data shown and statements made in this document are representative properties and characteristics. Actual results may differ, depending on use. Lydall makes no warranty, express or implied, concerning results which may be obtained by using the product.