

## Product Information for: P0350SPG

Fibre Blend:	Polyester	
Scrim Type:	Polyester Checkstatic	
Finish:	Superglaze	
Chemical Treatment:		
Weight (ISO 9073-1):	350 g/m <sup>2</sup>	
Thickness:	1.25 mm	
Permeability (ISO 9237):	250 l/dm <sup>2</sup> /min (420 mm/s) @ 200 Pa	
Electrical Resistance (DIN 54345-5):	0.01 MΩ (10 <sup>4</sup> Ω)	
	Machine	Cross
	Direction	Direction
Strength N / 5cm (ISO 9073-3):	1,300	1,200
Strain at 50N / 5cm (%) :	0.5	1.4
Strain at Peak (%) :	25.0	50.0
Shrinkage at 170°C (%) :	1.7	1.5

°Celsius	80	90	100	110	120	130	140	150	160	170	180	190	200	210	220	230	240	250	260	270	280	290
<b>NOTE: Working temperature limits may need to be reduced depending on gas chemistry</b>																						
ACIDS	ALKALIS	OXIDISING AGENTS	HYDROLYSIS	SOLVENTS	THE MOST VERSATILE OF THE LOW TEMPERATURE FIBRES. AVOID STRONG ALKALI, ACID AND HIGH HUMIDITY ENVIRONMENTS AT ELEVATED TEMPERATURES. USED WIDELY ACROSS MANY INDUSTRIES.																	
GOOD	FAIR	GOOD	POOR	GOOD																		
Maximum Continuous Temperature									Maximum Surge Temperature													

Revision Date: 19/03/2018

The data shown and statements made in this document are representative properties and characteristics. Actual results may differ, depending on use. Lydall makes no warranty, express or implied, concerning results which may be obtained by using the product.